

Andisil VS



typical properties*

VINYL POLYMERS

PRODUCT NAME	VINYL CONTENT	VISCOSITY
ANDISIL VS 6	3.00 mmoles/gm	6 cSt
ANDISIL VS 10	1.70 mmoles/gm	10 cSt
ANDISIL VS 20	1.20 mmoles/gm	20 cSt
ANDISIL VS 100	0.37 mmoles/gm	100 cSt
ANDISIL VS 200	0.25 mmoles/gm	200 cSt
ANDISIL VS 250	0.22 mmoles/gm	250 cSt
ANDISIL VS 400	0.19 mmoles/gm	400 cSt
ANDISIL VS 500	0.15 mmoles/gm	500 cSt
ANDISIL VS 1,000	0.11 mmoles/gm	1,000 cSt
ANDISIL VS 2,000	0.08 mmoles/gm	2,000 cSt
ANDISIL VS 4,000	0.07 mmoles/gm	4,000 cSt
ANDISIL VS 5,000	0.06 mmoles/gm	5,000 cSt
ANDISIL VS 10,000	0.05 mmoles/gm	10,000 cSt
ANDISIL VS 20,000	0.04 mmoles/gm	20,000 cSt
ANDISIL VS 65,000	0.03 mmoles/gm	65,000 cps
ANDISIL VS 80,000	0.024 mmoles/gm	80,000 cps
ANDISIL VS 100,000	0.02 mmoles/gm	100,000 cps
ANDISIL VS 165,000	0.015 mmoles/gm	165,000 cps

SPECIALTY POLYMERS

PRODUCT NAME	VINYL CONTENT	VISCOSITY
ANDISIL VDM 500	0.28 mmoles / gm	500 cSt
ANDISIL VDM 65,000	1.30 mmoles / gm	65,000 cP
ANDISIL MV 2,000	0.06 mmoles/gm	2,000 cSt

*These properties are not intended to be used as specifications but only as suggested characteristics

description - vinyl polymers

Andisil Vinyl Polymers are vinyl-terminated dimethyl-polysiloxanes that are available in a variety of viscosities. They can be used as base polymers or as blend polymers in order to create the desired hardness. These polymers can be cured with silicon-hydride crosslinkers and a platinum catalyst. Low volatility polymers are available upon request.

description - specialty polymers

Andisil VDM 500 & 65,000 Polymers are vinylmethyl-dimethyl polysiloxane copolymers that are also vinyl-terminated. The products have pendant vinyl groups along the polymer backbone to enhance the crosslinking density of the cured RTV (Room Temperature Vulcanization).

Andisil MV 2,000 polymer is a partially mono-functional vinyl polymer to reduce the durometer of the RTV formulation with minimal bleeding of fluid from the cured material. It may slow the curing of the RTV, but with the use of a faster platinum catalyst, it will help give a good normal cure.

storage & shelf life

The shelf life, when the container is stored unopened and under proper conditions (in temperatures above 35° – do not allow to freeze), is expected to be a minimum of twelve months.

packaging & handling

The Andisil Vinyl Polymers are supplied in 440 pound net weight steel lined drums, other packaging options are available upon request.

For additional information on the product, please contact your Sales Representative.



We believe that the information shown in this Product Bulletin to be an accurate description of the typical characteristics and/or uses of the product. Any suggestions of uses are not to be taken as an inducement to infringe any particular domestic or foreign patent. We recommend that the product be thoroughly tested for a specific application to determine the performance, efficacy and its safe handling and use.

AB Specialty Silicones • 3790 Sunset Avenue • Waukegan, IL 60087

phone 908.273.8015 • toll free 800.678.3024 • fax 908.273.8056 • email info@andisil.com